

PRELIMINARY AMENDMENT
U.S. Appln. No. 09/695,140

carboxylic acid random copolymer and a metal ion-neutralized olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer;

(B) 5 to 80 parts by weight of a fatty acid or fatty acid derivative having a molecular weight of at least 280; and

(C) 0.1 to 10 parts by weight of a basic inorganic metal compound capable of neutralizing acidic groups in components A and B.

13. A solid golf ball comprising a solid core of at least one layer and a cover of at least one layer enclosing the solid core, wherein at least one layer of the solid core or the cover is made of a golf ball material comprising a heated mixture having a melt index of at least 1.0 dg/min which is composed of:

C'
(A) 100 parts by weight of a base resin comprising a mixture of

(A1) an olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, or both of an olefin-unsaturated carboxylic acid random copolymer and an olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, and

(A2) a metal ion-neutralized olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, or both of a metal ion-neutralized olefin-unsaturated carboxylic acid random copolymer and a metal ion-neutralized olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer;

(B) 5 to 80 parts by weight of a fatty acid or fatty acid derivative having a molecular weight of at least 280; and

PRELIMINARY AMENDMENT
U.S. Appln. No. 09/695,140

C1 (C) 0.1 to 10 parts by weight of a basic inorganic metal compound capable of neutralizing acidic groups in components A and B.

16. A thread-wound golf ball comprising:

a thread-wound core composed of a solid center of at least one layer or a liquid center made of a liquid-filled center envelope, about which solid or liquid center has been wound a rubber thread, and

a cover of at least one layer which encloses the thread-wound core;

wherein the solid center or at least one layer of the cover is made of a golf ball material comprising a heated mixture having a melt index of at least 1.0 dg/min which is composed of:

(A) 100 parts by weight of a base resin comprising a mixture of

C2 (A1) an olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, or both of an olefin-unsaturated carboxylic acid random copolymer and an olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, and

(A2) a metal ion-neutralized olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer, or both of a metal ion-neutralized olefin-unsaturated carboxylic acid random copolymer and a metal ion-neutralized olefin-unsaturated carboxylic acid-unsaturated carboxylate random copolymer;

(B) 5 to 80 parts by weight of a fatty acid or fatty acid derivative having a molecular weight of at least 280; and

(C) 0.1 to 10 parts by weight of a basic inorganic metal compound capable of neutralizing acidic groups in components A and B.
